

Benefit from our strength. Use our intelligent chemical solutions as the key of added value



ISSUE

01 / 2010

Jan/Feb 2010

This Issue:

Pulcra
Innovation's

SHINE PLUS

with

Stabicryl SH

Products and
Full Process

Recipe for

SHINE PLUS

- Starting from Unwashed Jeans or Washed Jeans

Spray full garment:

STABICRYL SH + STABITEX ETR + black pigment

Curing: 150°C, 15 min

Stone-Wash: at room temperature with pumice stones and garment inside a net.

Rinsing: with net

Rinsing: without net

Washing: FORYL 3020 J

Softening: BELFASIN OET + ADASIL SM

Drying with silicone ball